



## PATENT ABSTRACTS OF JAPAN

(11) Publication number: **63103815 A**

(43) Date of publication of application: 09 . 05 . 88

(51) Int. Cl.

**C01B 33/18**(21) Application number: **61245599**

(22) Date of filing: 17 . 10 . 86

(71) Applicant: **KAWASAKI STEEL CORP**(72) Inventor: **FUNABASHI TOSHIHIKO  
UCHIMURA RYOJI**(54) **APPARATUS FOR CONTINUOUS PRODUCTION  
OF SiO FINE POWDER OR SUCH**

COPYRIGHT: (C)1988,JPO&amp;Japio

(57) Abstract:

**PURPOSE:** To obtain SiO powder in high efficiency, by using a continuous process maintained to a reduced pressure from the charge to the delivery in the heat-treatment of an SiO<sub>2</sub> oxide powder to generate SiO vapor and the recovery of condensed SiO powder.

**CONSTITUTION:** A raw material mixture 8 composed mainly of an SiO<sub>2</sub> oxide powder and containing a carbon-containing component or metallic silicon powder is continuously charged through hoppers 4a, 4b into a muffle 2. The mixture is heated in the muffle 2 with a heater 10 in a non-oxidizing atmosphere having reduced pressure to effect the reaction of SiO<sub>2</sub> with carbon or silicon in the raw material mixture and generate SiO vapor. At the same time, a non-oxidizing gas is introduced into the muffle 2 through gas inlet ports 17, 18 and the generated SiO vapor is condensed in a gaseous phase. At the same time, the condensed product is transferred to SiO powder recovery chambers 11, 12 via transfer pipes 8, 9 heated with the heater 10 and is recovered in the form of SiO powder.

